

TECHNICKÝ PÍSEK - ST 01/06

síta mm	zbytek		propad
	g	%	%
1,000	0	0	100,00
0,630	7,40	7,40	92,60
0,200	91,30	91,30	1,30
0,100	1,20	1,20	0,10
< 0,100	0,10	0,10	0,00
celkem	100	100	

MK_{calc} Střední velikost zrn mm	0,385
AFS	38,75
d₅₀ mm:	0,429
d₇₅ mm:	0,312
d₂₅ mm:	0,547
S_{th} Teoretický povrch cm²/g:	53,81
n_{th} Teoretický specifický počet zrn ks/g	18596,99

