

TECHNICKÝ PÍSEK - ST 05/10

síta mm	zbytek		propad
	g	%	%
1,250	0	0	100,00
1,000	5,00	5,00	95,00
0,500	94,00	94,00	1,00
< 0,500	1,00	1,00	0,00
celkem	100	100	

MKcalc Střední velikost zrn mm	0,726
AFS	19,76
d₅₀ mm:	0,761
d₇₅ mm:	0,628
S_{th} Teoretický povrch cm²/g:	29,78
n_{th} Teoretický specifický počet zrn ks/g	1999,59

