

## TECHNICKÝ PÍSEK - ST 06/12

síta	zbytek		propad
mm	g	%	%
1,600	0	0	100,00
1,250	6,00	6,00	94,00
1,000	0,00	0,00	94,00
0,630	93,00	93,00	1,00
< 0,630	1,00	1,00	0,00
<b>celkem</b>	<b>100</b>	<b>100</b>	

<b>MK<sub>calc</sub> Střední velikost zrn mm</b>	<b>0,829</b>
<b>AFS</b>	<b>17,09</b>
<b>d<sub>50</sub> mm:</b>	<b>0,825</b>
<b>d<sub>75</sub> mm:</b>	<b>0,725</b>
<b>S<sub>th</sub> Teoretický povrch cm<sup>2</sup>/g:</b>	<b>27,10</b>
<b>n<sub>th</sub> Teoretický specifický počet zrn ks/g</b>	<b>1384,49</b>

