

TECHNICKÝ PÍSEK - ST 03/08

vlhkost	0,2 % max
sypná hmotnost	1,50 t/m ³
pH	7,2

síta	zbytek		propad
mm	g	%	%
1,250	0	0	100,00
0,800	5,73	5,73	94,27
0,400	82,37	82,37	11,90
0,315	10,16	10,16	1,74
< 0,315	1,74	1,74	0,00
celkem	100	100	

MK_{calc} Střední velikost zrn mm	0,544
AFS	32,28
d₅₀ mm:	0,550
d₇₅ mm:	0,421
d₂₅ mm:	0,679
S_{th} Teoretický povrch cm²/g:	46,09
n_{th} Teoretický specifický počet zrn ks/g	74861,08

